

**OUR MOST VERSATILE HTV**

This low temperature versatile heat transfer vinyl adheres to a wide range of garments such as cotton, polyester, acrylic and even nylon! This thin and stretchy semi-matte finish material is soft on garments and great for any projects.



**APPLICATION INSTRUCTIONS**

- STEP 1** - Set design to cut, mirror on
- STEP 2** - Easily weed excess material
- STEP 3** - Set heat, time and pressure
- STEP 4** - Pre-press garment
- STEP 5** - Apply then peel hot or cold

**SPECIFICATIONS**

<b>WATER BASED</b>	No
<b>COMPOSITION</b>	PU
<b>THICKNESS</b>	75 micron
<b>CARRIER</b>	Adhesive & Transparent Polyester
<b>CUTTING</b>	Flex 45° blade
<b>CERTIFICATIONS</b>	OEKO TEX std 100 Class I: All references Class II: Ref 331, 326, 311, 332, 375 Vegan
<b>APPLICATIONS</b>	Cotton Polyester, Acrylic, Cotton, Polyester blend, Nylon (Polyamide) No repellent treatment
<b>TEMPERATURE</b>	285°F / 140°C 5 Sec Quick Mode 250°F / 120°C 20 Sec Low Temp <i>Specific textiles:</i> Nylon 1st press 285°F / 140°C 5 Sec Peel carrier Hot or Cold 2nd press 285°F / 140°C 15 Sec
<b>PRESSURE</b>	Medium
<b>PEEL</b>	Hot or Cold

**PRODUCT HIGHLIGHTS**

- Very thin, semi-matte finish vinyl
- Perfect for multiple garment applications
- Easy to weed, and peel hot or cold
- Suitable for all types of fabrics: cotton, polyester, and nylon
- Recommended for any applications on garments
- Suitable for elastane textiles such as sportswear garments
- Easy to cut, allowing intricate details

**CARE & MAINTENANCE**

- Always respect the garment instructions
- Wash warm up to 140°F/60°C or 100°F/40°C for Nylon
- Allow 24 hours after application before first wash
- Avoid the use of strong chemicals
- Wash inside out to extend the design's life
- Do not bleach
- Storage life recommendation is up to one year
- Store product in dry room with 60°-85°F / 15°-30°C
- Keep away from sunlight in a vertical position

**NOTE:** We highly recommend that you perform tests before production.



**Chemica US Corp.**

5300 Oakbrook Parkway | Building 300, suite 368 | Norcross, GA 30093 USA  
T +1 404-495-5991 | info@chemicaus.com | www.chemica-us.com